



CLIENT: SHIKOKU INTERNATIONAL CORPORATION

301 North Rampart Street, #C
Orange, CA 92868
Yoshiyuki Oyama

Test Report No: 1094930-3


Date: August 17, 2007

SAMPLE ID: The Client submitted and identified the following test material as KRM panels.
DATE OF RECEIPT: Entered into SGS USTC sample tracking system on July 3, 2007.
TESTING PERIOD: July 31, 2007.
AUTHORIZATION: Testing authorized by Yoshiyuki Oyama.
TEST REQUESTED: Perform standard flame spread and smoke density developed classification tests on the sample supplied by the Client in accordance with ASTM Designation E84-07 "Standard Method of Test for Surface Burning Characteristics of Building Materials". The foregoing test procedure is comparable to UL 723, ANSI/NFPA No. 255, and UBC No. 8-1.

TEST RESULTS:	<u>Flame Spread</u>	<u>Smoke Density</u>
	5	10


For detailed results see page 2.

Tested by



Brian Ortega
Test Technician

**Signed for and on behalf of
SGS U.S. Testing Company Inc.**



Greg Banasky
Supervisor Fire Technology

Page 1 of 2

This report is issued by SGS U.S. Testing Company Inc. under its General Conditions for Testing Services (copy available on request). SGS U.S. Testing's responsibility under this report is limited to proven negligence and will in no case be more than the amount of the testing fees. Except by special arrangement, samples are not retained by SGS U.S. Testing for more than 30 days. The results shown on this test report refer only to the sample(s) tested unless otherwise stated, under the conditions agreed upon. Anyone relying on this report should understand all of the details of the engagement. Neither the name, seals, marks nor insignia of SGS U.S. Testing may be used in any advertising or promotional materials without the prior written approval of SGS U.S. Testing. The test report cannot be reproduced, except in full, without prior written permission of SGS U.S. Testing Company Inc.



CLIENT: SHIKOKU INTERNATIONAL CORPORATION

Report No.: 1094930-3
Date: August 16, 2007
Page: 2 of 2

PREPARATION AND CONDITIONING: PREPARATION AND CONDITIONING: The sample material was supplied in three pieces, 22" wide by 96" long.

Prior to testing, the specimen was placed in the conditioning room (maintained at $73.4 \pm 5^\circ$ F and a relative humidity of $50 \pm 5\%$) and allowed to reach moisture equilibrium.

E 84 TEST DATA SHEET:

CLIENT: Shikoku International Corporation DATE: 07/31/07

SAMPLE: KRM panels

FLAME SPREAD:

IGNITION: 1 minute, 30 seconds

FLAME FRONT: 1 foot maximum

TIME TO MAXIMUM SPREAD: 2 minutes, 15 seconds

TEST DURATION: 10 minutes

CALCULATION: $8.09 \times 0.515 = 4.17$

SUMMARY: FLAME SPREAD: 5 SMOKE DENSITY: 10

SUMMARY OF ASTM E84 RESULTS: Because of the possible variations in reproducibility, the results are adjusted to the nearest figure divisible by 5. Smoke Density values over 200 are rounded to the nearest figure divisible by 50.

In order to obtain the Flame Spread Classification, the above results should be compared to the following table:

<u>NFPA CLASS</u>	<u>UBC CLASS</u>	<u>FLAME SPREAD</u>	<u>SMOKE DEVELOPED</u>
A	I	0 through 25	Less than or equal to 450
B	II	26 through 75	Less than or equal to 450
C	III	76 through 200	Less than or equal to 450

BUILDING CODES CITED:

1. National Fire Protection Association, ANSI/NFPA No. 101, "Life Safety Code", 1994 Edition.
2. Uniform Building Code, 1994 Edition, Chapter 8, Interior Finishes, Sections 801-807.

End of Report